

E-mail: info@dansand.dk
Tel: +45 8682 5811

Variant:

Product designation: Kiln-dried silica sand

 Responsible:
 Afdelingschef - QHSE, Morten Grundvad

 Item number:
 210025, 210125, 210126, 210150, 211000,

396820

Producer: DANSAND A/S, Lervejdal 8B, 8740 Brædstrup

# Sand for sand blasting

# High quality sand for sand blasting

# Description

For sandblasting, we offer a selection of different types of sand. All with the high quality as a common denominator.

#### OVEN-DRIED SILICA SAND

Our oven-dried silica sand is a cost-effective sandblasting agent that effectively removes unwanted coating and leaves a clean surface, ready for finishing. The silica sand is available in two grades, suitable for both dry and wet sand blasting.

- Dansand® no. 50B 0.36-1.00 mm is our best-selling type of sand and is used for concrete, masonry and iron constructions.
- Dansand® no. 100 0.36-2.00 mm is suitable for stripping rust or fouling from very rough surfaces.

#### **ASILIKOS**

Asilikos is a fantastic material for silicosis-free sand blasting and can even be recycled. The product is available in different grain sizes and packaging sizes on request. NASTRA COPPER SILICATE

Nastra copper silicate (Fe-silicate) is used for silicosis-free sand blasting and is available in different grain sizes and packaging sizes on request.

# Specifications

### **DECLARATION**

Product name: Dansand® no. 50B (0.36-1.00 mm)
Product description: Oven-dried silica sand

Product number: 396820 DECLARED VALUES

Properties Test method Expected value Variation range

Bulk density - kg/m³ DS/EN 1097-3 1430 1400-1500

15.11.25 Page: 1



Density – kg/m³	DS/EN 1097-6	2640	2620-2660
Hardness - MOHS		7	-
Medium grain size - mm		0.48	-
Grain shape		Rounded edge	
SiO2 - %		98 %	> 96 %

Product name: Dansand® no. 100 (0.36-2.00 mm)

Product description: Oven-dried silica sand

Product number: 210125, 210126, 210150, 211000, 210025

**DECLARED VALUES** 

Properties	Test method	Expected value	Variation range
Bulk density – kg/m³	DS/EN 1097-3	1450	1400-1500
Density – kg/m³	DS/EN 1097-6	2640	2620-2660
Hardness - MOHS		7	-
Medium grain size - mm		0.85	-
Grain shape		Rounded edge	
SiO2 - %		98 %	> 96 %

Analysis data should be considered as guidance only. The raw material is a natural product whose composition may vary.

## **STORAGE**

Dry, covered and without risk of contamination.

## **DELIVERY**

The products are delivered in bags of 25 kg or 1000 kg big bags. By agreement, some of the products can also be delivered loose in a silo truck.

## **ENVIRONMENTAL INFORMATION AND DISPOSAL**

Packaging and used sand blasting material should be disposed of in accordance with local requirements.

# **Documentation & Application**

#### **APPLICATION**

Sandblasting of surfaces on concrete, masonry and iron

#### **DOWNLOADS**

Asilikos

15.11.25 Page: 2



structures.

Always perform sandblasting with approved safety equipment. Always follow applicable rules.



## Sand for sand blasting

Variants: Dansand® nr. 100 (0,36-2,00 mm) - 210125, 210126, 210150, 211000, 210025, Dansand® nr. 50B (0,36-1,00 mm) - 396820

15.11.25 Page: 3