


General characteristics	Method	Typical value	Range
Bulk density. Kg/m³	EN 12902	1580	1530-1630
Disparity - D60/D10	EN 12902	1,3	<1,5
Chloride content - %	EN 1744-1	0,012	

Sieve size - mm	1	0,9	0,8	0,71	0,63	0,5	0,4	0,355	0,315	0,25	0,125	0,063
Passing - weight WT%	100	100	100	99,7	92,0	28,0	2,0	0,4	0,2	0,0	0,0	0,0



Chemical analysis						
Type	Fe ₂ O ₃	Al ₂ O ₃	K ₂ O	CaO	Na ₂ O	SiO ₂
Weight WT%	0,127	0,848	0,389	0,07	0,15	98

Supplier declaration

DANSAND A/S declares that the materials above meets the requirements of the agreement of EN 12904:2005

Responsible: QHSE Manager Morten Grundvad