


General characteristics	Method	Typical value	Range
Bulk density. Kg/m³	EN 12902	1605	1550-1650
Disparity - D60/D10	EN 12902	1,3	<1,5

Sieve size - mm	1	0,9	0,8	0,71	0,63	0,5	0,4	0,355	0,315	0,25	0,125	0,063
Passing - weight WT%	100	98	90	71	39	6	1	0	0	0	0	0



Chemical analysis						
Type	Fe ₂ O ₃	Al ₂ O ₃	K ₂ O	CaO	Na ₂ O	SiO ₂
Weight WT%	0,117	0,66	0,322	0,056	0,102	98,59

Supplier declaration

DANSAND A/S Declares the the materials above meets the requirements of the agreement of EN 12904:2005

Responsible: QHSE Manager Morten Grundvad