


Gernal characteristics	Method	Typical value	Range
Bulk density . Kg/m³	EN 12902	1622	1580-1650
Disparity - D60/D10	EN 12902	1,3	<1,5

Sieve size - mm	2,5	2,24	2	1,8	1,6	1,4	1,25	1,12	1	0,9	0,8	0,71
Passing - Weight WT%	100	100	100	100	100	100	95	75	47	23	9	4



Chemical analysis						
Type	Fe ₂ O ₃	Al ₂ O ₃	K ₂ O	CaO	Na ₂ O	SiO ₂
Weight WT%	0,166	0,618	0,289	0,073	0,11	98,35

Supplier declaration:

DANSAND A/S declares that the materials above meets the requirements of the agreement of EN 12904:2005

Responsible: QHSE Manager Morten Grundvad