


Gernal characteristics	Method	Typical value	Range
Bulk density . Kg/m³	EN 12902	1630	1580-1650
Disparity - D60/D10	EN 12902	1,4	<1,5

Sieve size - mm	2,5	2,24	2	1,8	1,6	1,4	1,25	1,12	1	0,9	0,8	0,71
Passing - weight WT%	100	100	100	99	92	74	56	37	18	7	3	1



Chemical analysis						
Type	Fe ₂ O ₃	Al ₂ O ₃	K ₂ O	CaO	Na ₂ O	SiO ₂
Weight WT%	0,123	0,544	0,215	0,076	0,107	98,56

Supplier declaration:

DANSAND A/S declares that the materials above meets the requirements of the agreement of EN 12904:2005

Responsible: QHSE Manager Morten Grundvad