


General characteristics	Method	Typical value	Range
Bulk density . Kg/m³	EN 12902	1574	1525-1630
Disparity - D60/D10	EN 12902	1,3	<1,5

Sieve size - mm	2,5	2,24	2	1,8	1,6	1,4	1,25	1,12	1	0,9	0,8	0,71
Passing - weight WT%	98	87	61	31	12	4	3	2	2	2	1	1



Chemical analysis						
Type	Fe ₂ O ₃	Al ₂ O ₃	K ₂ O	CaO	Na ₂ O	SiO ₂
Weight WT%	0,228	0,935	0,348	0,173	0,191	97,58

Supplier declaration - DANSAND A/S:

The material above comply whit the requirements in EN 12904:2005

Responsible: QHSE Manager Morten Grundvad