


General characteristics	Method	Typical value	Range
Bulk density. Kg/m ³	EN 12902	1579	1530-1630
Disparity - D60/D10	EN 12902	1,2	<1,5

Sieve size - mm	7,1	6,3	5,6	5	4,5	4	3,55	3,15	2,8	2,5	2,24	2
Passing - weight WT%	100	100	97	87	69	36	10	3	1	1	1	1



Chemical analysis						
Type	Fe ₂ O ₃	Al ₂ O ₃	K ₂ O	CaO	Na ₂ O	SiO ₂
Weight WT%	1,663	5,531	1,596	1,136	1,457	86,49

Supplier declaration - DANSAND A/S:

The material above comply whit the requirements in EN 12904:2005

Responsible: QHSE Manager Morten Grundvad