


Gernal characteristics	Method	Typical value	Range
Bulk density . Kg/m³	EN 12902	1520	1470-1570
Disparity - D60/D10	EN 12902	1,3	<1,5

Sieve size - mm	9	8	7,1	6,3	5,6	5	4,5	4	3,55	3,15	2,8	2,5
Passing - weight WT%	99	93	77	48	18	8	5	4	3	3	2	2



Chemical analysis						
Type	Fe ₂ O ₃	Al ₂ O ₃	K ₂ O	CaO	Na ₂ O	SiO ₂
Weight WT%	1,732	5,152	1,525	1,307	1,331	86,85

Supplier declaration - DANSAND A/S:

The material above comply whit the requirements in EN 12904:2005

Responsible: QHSE Manager Morten Grundvad